

**CLASSIC BS 2,7 mm**

Characteristics EN 12199	Standard	Unit	Requirements	Average values from production
Hardness	ISO 7619	shore A	≥ 70	90 ± 5
Residual indentation	EN 433	mm	≤ 0,20	0,08
Abrasion resistance	ISO 4649 (Met. A-5N)	mm <sup>3</sup>	≤ 250	140
Dimensional stability	EN 434	%	± 0,40 max	± 0,30
Flexibility	EN 435 Met. A (Ø 20mm)	-	no fissuring	comply
Colour fastness to artificial light	ISO 105-B02 Met. 3	degree	≥ 6 blue scale ≥ 3 grey scale	comply
Cigarette burn	EN 1399	rating	met. A ≥ 4 met. B ≥ 3	comply
Tear strength	ISO 34-1 Met. B, procedure A	N/mm	≥ 20	comply
<b>Characteristics EN 14041</b>				
Fire behaviour	EN 13501-1	class	-	B <sub>fl</sub> -s1
Slip resistance	EN 13893	class	≥ 0,30 (DS)	DS
<b>Other characteristics</b>				
Resistance to stains	EN 423	-	-	resistant *
Thermal resistance	DIN 52612	m <sup>2</sup> K/W	-	0,015
Electrical resistance	EN 1081 Met. A	ohm	-	> 10 <sup>10</sup>
Electrostatic charge	EN 1815	kV	-	≤ 2 (antistatic)
Reduction of sound due to treading	ISO 10140-3	dB	-	approx. 8
Castor chairs	EN 425	-	-	suitable for W castors
<b>Environmental characteristics</b>				
VOC emissions	CA Section 01350	-	various	comply
VOC emissions	AgBB	-	various	comply

\* depending on concentration and time of contact, for specific agent please ask.



2,7 mm

3,8 kg/m<sup>2</sup>

50 x 50 cm

**Classification EN 685:**

Technical data are subject to change without notice. Rev. 1/13