

**ZEUS ANT48 3,5 mm**

Characteristics EN 12199	Standard	Unit	Requirements	Average values from production
Hardness	ISO 7619	shore A	≥ 70	85
Residual indentation	EN 433	mm	≤ 0,25	0,15
Abrasion resistance	ISO 4649 (Met. A - 5N)	mm <sup>3</sup>	≤ 250	160
Dimensional stability	EN 434	%	± 0,40 max	± 0,30
Flexibility	EN 435 Met. A (Ø 20mm)	-	no fissuring	comply
Colour fastness to artificial light	ISO 105-B02 Met. 3	degree	≥ 6 blue scale ≥ 3 grey scale	comply
Cigarette burn	EN 1399	rating	met. A ≥ 4 met. B ≥ 3	comply
Tear strength	ISO 34-1 Met. B, procedure A	N/mm	≥ 20	comply
<b>Characteristics EN 14041</b>				
Fire behaviour	EN 13501-1	class	-	B <sub>n</sub> -s1
Slip resistance	EN 13893	class	≥ 0,30 (DS)	DS
Electrical resistance	EN 1081 Met. A	ohm	10 <sup>6</sup> ≤ R <sub>t</sub> ≤ 10 <sup>9</sup> (static dissipative)	comply
<b>Other characteristics</b>				
Toxicity of decomposition gases	DIN 53436 at 350°C	-	-	not toxic
Resistance to stains	EN 423	-	-	resistant *
Ramp slip resistance	DIN 51130	°	BGR 181	≥ 6 (R9)
Thermal resistance	DIN 52612	m <sup>2</sup> K/W	-	0,022
Electrostatic charge	EN 1815	kV	-	≤ 2 (antistatic)
Reduction of sound due to treading	ISO 10140-3	dB	-	up to 12
Castor chairs	EN 425	-	-	suitable for W castors
<b>Environmental characteristics</b>				
VOC emissions	AgBB	-	various	comply

\* depending on concentration and time of contact, for specific agent please ask.

**CE** EN 14041 DoP\_007



3,5 mm




5,6 kg/m<sup>2</sup>



100 x 100 cm



≤10<sup>9</sup>Ω dissipative flooring

**Classification EN 685:**

The data declared by the manufacturer shall be taken as average: single values change amongst batches and colours.